



Product Information

AkzoNobel
Tomorrow's Answers Today

Bermocoll M 800 X

BERMOCOLL M 800 X is a non-ionic, water soluble cellulose ether. It improves the consistency, the stability, and the water retention of water based products.

BERMOCOLL M 800 X can also be used in gypsum-based glues and crack fillers. For this application, a suitable concentration is 0.3 - 0.6 %.

BERMOCOLL M 800 X should be admixed in dry form before the water is added. Due to its particle size BERMOCOLL M 800 X will dissolve rapidly after addition of water to the dry mix.

Specifications

BERMOCOLL M 800 X is a high viscosity grade of methyl ethyl hydroxyethyl cellulose.

Physical data

Appearance	whitish powder
Particle size	98 % < 450 µm
Water content	max 4 %
Salt content	max 6 %

Characteristics of aqueous solutions

pH (1 % solution)	neutral
Surface activity	weak
Viscosity at 20°C (Brookfield LV) 1 % solution	10,000 - 14,000 mPa·s

Packaging and Storage

BERMOCOLL M 800 X is packed in multiply paper bags with an inner polyethylene bag. Net weight 20 kg (approx. 44 lbs). We recommend emptying the bags from the bottom. The empty bags can be recycled or burned. In unopened bags, BERMOCOLL M 800 X can be stored for several years. In opened bags, the moisture content of BERMOCOLL M 800 X will be influenced by the air humidity.

At the temperatures above 250°C (480°F), charring of BERMOCOLL M 800 X will occur. At high temperatures and in contact with an open flame, BERMOCOLL M 800 X will burn slowly with the characteristics of cellulose.

Applications

BERMOCOLL M 800 X is used in cement-based tile fix and joint mortars for improvement of workability, consistency, water retention and adhesion. Normal dosage in mortars is 0.2 - 0.5 % calculated on the dry mortar weight.

CCD 2806