



## Product Information

**AkzoNobel**  
Tomorrow's Answers Today

### Bermocoll EHM 200

BERMOCOLL EHM 200 is an associative non-ionic, water-soluble cellulose ether that improves the rheological properties of water based paints.

#### Specifications

BERMOCOLL EHM 200 is a hydrophobically modified ethyl hydroxyethyl cellulose.

#### Physical data

Appearance	whitish powder
Particle size	98 % < 500 µm
Water content	max 4 %
Salt content	max 4.5 %

#### Characteristics of aqueous solutions

Solution appearance	opaque
pH (1 % solution)	neutral
Surface activity	weak
Viscosity at 20°C (Brookfield LV) 1 % solution	min 350 mPa·s

#### Applications

BERMOCOLL EHM 200 is used as a thickener in all types of latex paints, intended for interior as well as for exterior use. BERMOCOLL EHM 200 improves high shear viscosity, roller spatter, flow and levelling. BERMOCOLL EHM 200 has a high resistance to enzymatic degradation. Normal dosage is 0.3 - 0.5 % calculated on the total paint weight.

In order to facilitate dispersion in water, BERMOCOLL EHM 200 has been treated to give a pH-dependent dissolving. It should be added to neutral or slightly acid water. To speed up the dissolving process, pH should be increased to above 8 by using alkaline ingredients such as ammonia or alkaline pigment dispersants.

If adjustment of the final paint viscosity is necessary, a highly concentrated slurry either in water or in an organic solvent should be used. It is not recommended to add the product as a dry powder after pigment grinding. Under the alkaline pH conditions at that stage BERMOCOLL EHM 200 will dissolve too rapidly with the risk of lump formation.

#### Packaging and Storage

BERMOCOLL EHM 200 is packed in multiply paper bags with an inner polyethylene bag. Net weight 20 kg or 50 lbs for the American market. We recommend emptying the bags from the bottom. The empty bags can be re-cycled or burned. In unopened bags, BERMOCOLL EHM 200 can be stored for several years. In opened bags, the moisture content of BERMOCOLL EHM 200 will be influenced by the air humidity.

At temperatures above 250°C (480°F), charring of BERMOCOLL EHM 200 will occur. At high temperatures and in contact with an open flame, BERMOCOLL EHM 200 will burn slowly with the characteristics of cellulose.

CCD 0904