



BERMOCOLL E 351 FQ

BERMOCOLL E 351 FQ is a non-ionic, water soluble cellulose ether. It improves the consistency, the stability, and the water retention of water based products.

Specifications

BERMOCOLL E 351 FQ is a medium viscosity grade of ethyl hydroxyethyl cellulose.

Physical data

Appearance	whitish powder
Particle size	98 % < 500 µm
Water content	max 4 %
Salt content	max 5 %

Characteristics of aqueous solutions

pH (1 % solution)	neutral
Surface activity	weak
Viscosity at 20°C (Brookfield LV)	
2 % Solution	4,250 - 6,000 mPa·s

Applications

BERMOCOLL E 351 FQ is used in **latex paints** for thickening and stabilizing effects. Normal dosage in paints is 0.2 - 0.5 % calculated on the total paint weight.

BERMOCOLL E 351 FQ is used in **cement-based tile fix and joint mortars** for improvement of workability, consistency, water retention and adhesion. Normal dosage is 0.2 – 0.7 % calculated on the dry mortar weight.

BERMOCOLL E 351 FQ is easily dispersed in cold water of pH7 or less. BERMOCOLL E 351 FQ can form lumps when added to an alkaline liquid. To avoid this, it should be added as a ready stock solution, as a slurry in slight acid water or in an organic solvent, or as a dry mix with other powder materials.

The dissolving time after dispersion is influenced by the water pH. Alkaline additives can be used to speed up the dissolving process.

Packaging and Storage

BERMOCOLL E 351 FQ is packed in multiply paper bags with an inner polyethylene bag. Net weight 20 kg (approx 44 lbs). We recommend emptying the bags from the bottom. The empty bags can be recycled or burned. In unopened bags, BERMOCOLL E 351 FQ can be stored for several years. In opened bags, the moisture content of BERMOCOLL E 351 FQ will be influenced by the air humidity.

At the temperatures above 250°C (480°F), charring of BERMOCOLL E 351 FQ will occur. At high temperatures and in contact with an open flame, BERMOCOLL E 351 FQ will burn slowly with the characteristics of cellulose.

CCD 3709

No representation or warranty, expressed or implied, is made as to the accuracy or completeness of the information or data contained herein and AkzoNobel Functional Chemicals shall have no obligation or liability whatsoever with respect to any such information or data, including, but not limited to, any liability for infringement of patent or other industrial property rights. AkzoNobel Functional Chemicals disclaims all implied warranties of merchantability and fitness for a particular purpose. AkzoNobel Functional Chemicals shall in no event be liable for incidental or consequential damages, including, without limitation, lost profit, loss of income, loss of business opportunity and any other related costs and expenses.