



# Product Data Sheet


## Thioplast™ EPS 70

### Epoxidized Polysulfides

Status:  
January 2010

**Intended use** Formulation of flexible and corrosion-resistant coatings, adhesives and sealants

**Description** Epoxy-terminated Polymer  
R = chain with Polysulfide structure  
R' = resins of glycidyl ether of  
Bisphenol A (DGEBA)



**Properties** Polymer of low viscosity  
Viscosity (25°C) – Pa\*s approx. 7.5  
Appearance Clear, amber liquid  
Colour yellow  
Epoxy-oxygen content - wt-% approx. 5  
Equivalent weight - g/equ approx. 310

**Application** EPS 70 is used for manufacturing of flexible, crack bridging and corrosion-resistant coatings for concrete and steel. Further EPS 70 is applied for the formulation of adhesives, sealants and as reactive diluents.

EPS types combine the well known properties of common Polysulfide polymers with improved surface adhesion and faster curing. Further advantages are:

- Extended flexibility
- Improved impact and thermal shock resistance
- Excellent water and corrosion resistance
- Resistance to a number of aggressive chemicals, fuels and other oil products.

EPS 70 is used in two-component systems and can be cured at room temperature. Typical hardeners are aliphatic and cycloaliphatic amines.

**Packaging** EPS 70 is usually supplied in 216,5 l drums (57 USG). Other packaging available.

**Storage** Protect against contact with air, moisture and temperatures over 30°C during transportation and storage. Containers should be firmly sealed after each use.

Under appropriate storage conditions the shelf life of this product is 6 months

**Handling** Full information on the safe handling of EPS 350 is available in the Material Safety Data Sheet (MSDS). Further details are available upon request.

**Legal Disclaimer:** All information, appearing in this sheet is based upon tests and data believed to be reliable, however, it is the user's responsibility to determine the suitability for his own use of the products described here. Nothing herein contained is to be construed as permission or as a recommendation to infringe any patent. All orders accepted shall be subjected to the standard conditions of sale of the manufacturing company, Akzo Nobel Functional Chemicals GmbH & Co. KG.

Akzo Nobel Functional Chemicals  
GmbH & Co. KG  
Liebigstr.7  
07973 Greiz  
Tel. +49-3661-78-0  
thioplast@akzonobel-chemicals.com  
www.thioplast.com